

Chrom-Effekt

product information

26.08.2024 V1

AP-Merit Chrome Effect creates a metallic look, like polished aluminum. Suitable for painting wheel rims, add-on parts, decorative strips or for partial and complete painting. Coverage: approx. 6-8 m²/l (depending on the effect)

Features

Colour:	Liquid Silver
Mixing ratio:	Ready for use
Hardener:	not required
Thinner:	not required

Processing

	Nozzle: 1.0 mm Pressure: 2.0-4.0 bar	HVLP	Nozzle: 1,0-1,3 mm Pressure: 2,0-4,0 bar
RP	Sprayer pressure: 0.7 bar		Sprayer pressure: 0,7 bar
	1-2 thin spray coats		- Flash-off time between
()	2-3 thin spray coats for	<u>((t/t/</u>)	spray coats is
	large surfaces		2-5 minutes
	3 – 6 μm		12 s
(†)		()	4 mm DIN /20°C

Drying

	20°C	Approx. 30 minutes at 20°C	60°C	Approx. 10 minutes at 60°C
For large areas, drying at 60°C is recommended in any case.				

Further processing

Γ•	After drying, AP-Merit Chrome Effect can be painted over with 2K clear	
•	coats (e.g.: AP-Merit 7525 UHS Premium clear coat).	

Notes



- The substrate must be primed in black. For the best effect, a 2K uni top coat is recommended. The substrate must not be sanded again. If necessary, polish out any imperfections.
- When applying the chrome effect paint, it is important to ensure that the paint is applied very thinly and evenly. It is recommended that the effect paint is carefully sprayed on. Less is more! Do not apply layers that are too wet!
- MASTER TIP: To get the exact effect, always create a spray pattern in advance. The more black shines through, the more pronounced the effect!
- Application temperature: from + 18°C



Store in a dry and frost-free place. Can be stored for at least 12 months in the sealed original container.

This data sheet is for information purposes only! To the best of our knowledge, the information corresponds to the state of the art and is based on many years of experience in the manufacture of our products. However, the information is non-binding and without guarantee.

Wolfgang GesmbH. – www.ap-merit.com – office@ap-merit.com -Tel.: +43 5576 72330